

Experimental study of ^{199}Hg spin anti-relaxation coatings

Journal Article

Author(s):

Chowdhuri, Zema; Fertl, Martin; Horras, Marlon; Kirch, Klaus; Krempel, Jochen; Lauss, Bernhard; Mtchedlishvili, Alexander; Rebreyend, Dominique; Roccia, Stéphanie; Schmidt-Wellenburg, Philipp; Zsigmond, Géza

Publication date:

2014-05

Permanent link:

<https://doi.org/10.3929/ethz-b-000078524>

Rights / license:

[In Copyright - Non-Commercial Use Permitted](#)

Originally published in:

Applied Physics B 115(2), <https://doi.org/10.1007/s00340-013-5598-8>

Experimental study of ^{199}Hg spin anti-relaxation coatings

Z. Chowdhuri · M. Fertl · M. Horras · K. Kirch · J. Krempel · B. Lauss ·
A. Mtchedlishvili · D. Rebreyend · S. Roccia · P. Schmidt-Wellenburg ·
G. Zsigmond

Received: 27 May 2013 / Accepted: 23 July 2013 / Published online: 3 August 2013
© Springer-Verlag Berlin Heidelberg 2013

Abstract We report on a comparison of spin relaxation rates in a ^{199}Hg magnetometer using different wall coatings. A compact mercury magnetometer was built for this purpose. Glass cells coated with fluorinated materials show longer spin coherence times than if coated with their hydrogenated homologues. The longest spin relaxation time of the mercury vapor was measured with a fluorinated paraffin wall coating.

1 Introduction

Magnetometers using optically pumped spin populations of atoms to measure magnetic fields have achieved sensitivities comparable to most superconducting quantum interference devices (SQUIDs)-based magnetometers during the last decades [1]. Mercury magnetometers (HgMs), first used for searches of a ^{199}Hg electric dipole moment (EDM) [2, 3] and later as a cohabiting magnetometer in a neutron EDM (nEDM) search [4], are based on the optical detection of the Larmor precession with a frequency ω_L of spin-1/2 ^{199}Hg atoms in a magnetic field B :

$$\omega_L = \gamma \cdot B, \quad (1)$$

where γ_{Hg} is the gyromagnetic factor of ^{199}Hg . An intrinsic advantage of measuring a free induction decay is that the precession frequency is directly related to the absolute magnitude of the magnetic field. The sensitivity δB of an optical magnetometer is proportional to $(\tau TN)^{-1/2}$, where τ is the spin coherence time also referred to as the depolarization time, T the observation time, and N is the number of atoms. However, in the case of a ^{199}Hg magnetometer, we expect photon shot noise to dominate the sensitivity δB_p given by, e.g., equation (25) in Ref. [5] for an exponentially decaying sinusoidal signal. This means $\delta B_p \propto a_n/a_s$ where a_s is the initial signal amplitude of the sine and a_n is the RMS noise amplitude. In the case of homogeneous fields, the decay time constant τ is dominated by depolarization of ^{199}Hg atoms during collisions with the walls confining the atomic vapor. Our study was motivated by magnetic field monitoring requirements needed for an improved search of a nEDM [6] at the Paul Scherrer Institut (PSI). As the statistical sensitivity increases, the experiment also needs an improved control and monitoring of magnetic field stability to assess field drifts on a comparable sensitivity level.

In the PSI nEDM apparatus, a batch of ^{199}Hg vapor is polarized in a dedicated cell, while the spin precession of neutrons and a previously prepared batch of mercury is measured in the adjacent main precession chamber. At the start of each new measurement cycle, the polarized ^{199}Hg vapor is released into the precession chamber where a $\pi/2$ -flip starts the Larmor precession. Decreasing the depolarization rate due to wall collisions in the separate polarizing cell is a promising path to higher sensitivity as this will increase the equilibrium polarization before release, and hence the signal amplitude a_s .

Z. Chowdhuri · M. Fertl · M. Horras · K. Kirch · B. Lauss ·
A. Mtchedlishvili · P. Schmidt-Wellenburg (✉) · G. Zsigmond
Paul Scherrer Institut, Villigen, Switzerland
e-mail: philipp.schmidt-wellenburg@psi.ch

K. Kirch · J. Krempel
ETH Zurich, Zurich, Switzerland

D. Rebreyend
LPSC, Université Joseph Fourier Grenoble 1, CNRS/IN2P3,
Grenoble INP, Grenoble, France

S. Roccia
CSNSM, CNRS/IN2P3, Université Paris Sud, Orsay, France

In the past low viscosity Fomblin¹, oil of type “Y” was used to coat the glass polarization cell. Over the course of weeks, the high surface tension of this type of Fomblin oil causes the film to pull away and expose sections of the bare glass. Re-coating of the cell requires venting of the apparatus and the disassembly of the mercury magnetometer, a lengthy and tedious process. In order to find a better material which would minimize these regular interventions, we decided to study alternative anti-relaxation coatings. A dedicated mercury magnetometer was built at PSI [7] to study depolarization times τ of several different wall coatings.

2 Technical description of the mercury magnetometer

Figure 1 shows a sketch of the mercury magnetometer test bench. The central part of the magnetometer is a glass cell that can be filled with ¹⁹⁹Hg atomic vapor. In contrast to other experiments [8, 9], the cell was not sealed off, but remained connected via two valves to the vacuum system and a mercury vapor source. It was placed in the center of a three-layer cylindrical magnetic shield without end caps, which provided a shielding factor of ~ 500 along the axis and $\sim 2,000$ perpendicular to it. One circular polarized light beam along the cylinder axis was used for both spin pumping and detection of the spin precession. For optical spin pumping, a magnetic field B_0 , aligned with the light direction, was generated with a solenoid wound on a polyvinyl chloride (PVC) cylinder inside the innermost shield. The coil has a length of 1,600 mm and consists of 760 windings. A 1.6-mA current was used to generate a field of $1 \mu\text{T}$ with a measured inhomogeneity of $\Delta B/B_0 \approx 3 \times 10^{-3}$. A magnetic field of 50 nT was measured with the coil turned off. After optical pumping, the spins were aligned with the pumping field B_0 and had to be flipped to measure a Larmor precession. To do this, we turned the main magnetic field direction non-adiabatically by almost $\pi/2$ by rapidly ramping up a second, static field $B_1 \approx 4 \mu\text{T}$, perpendicular to B_0 . The coil producing this field is a saddle coil consisting of ten frames, with three windings each, mounted on the same PVC tube as the B_0 -coil. After the B_1 field was turned on, the spins started precessing in the effective field $\mathbf{B}_{\text{eff}} = \mathbf{B}_0 + \mathbf{B}_1$ that had a measured inhomogeneity of $\Delta B/B \approx 2 \times 10^{-3}$ within the cell region.

2.1 Optical pumping

We used the same ²⁰⁴Hg discharge UV ($\lambda \approx 254 \text{ nm}$) lamp for optical pumping and readout. A quartz bulb filled with




Fig. 1 Schematic of the setup used to investigate several different materials as anti spin relaxation coatings. 1 Hg cell, 2 1/4-wave plate, 3 Brewster plate for linear polarization, 4 lens, 5 discharge ²⁰⁴Hg bulb and microwave cavity, 6 microwave generator, 7 DAQ and control system, 8 photo multiplier tube, 9 magnetic shield, 10 ¹⁹⁹Hg source, 11 vacuum pump, 12 vacuum and Hg vapor handling system. The pressure was measured with full-range pressure gauges (Pfeiffer PKR 251) at positions *a*, *b*, and *c*

²⁰⁴Hg vapor was mounted inside a microwave cavity driven by a microwave generator such that a continuous plasma discharge was maintained. The cavity was mounted on a three-axis micrometer table for fine adjustment of the spatial position. The light source was mounted at the focus of a lens with a focal length of 15 cm to obtain a nearly parallel light beam. Both optically spin pumping the ¹⁹⁹Hg vapor and reading the precession signal need circularly polarized light. The light was linearly polarized with a Brewster thin-film polarizer,² by reflection under the Brewster angle Θ_b . A quarter-wave plate in the light path between the Brewster plate and the mercury vapor cell turned the linearly polarized light into circularly polarized. The quarter-wave plate could be adjusted to $\pm 1^\circ$ to the polarization plane of the linear polarized light giving a circular polarization of the light larger than 96 %.

All optical elements have a diameter of 50 mm and could be adjusted relative to the position of the ¹⁹⁹Hg cell inside the magnetic shield. The light was detected by a photomultiplier³ (PM), operated at 400 V at the far end of the shield.

Before operation, the whole system was evacuated to pressures of $1 \times 10^{-5} \text{ mbar} < p_{b,c} < 2 \times 10^{-5} \text{ mbar}$ and $p_a < 1 \times 10^{-6} \text{ mbar}$ over two days (see Fig. 1 for gauge positions). During operation, mercury vapor was delivered from the ¹⁹⁹Hg source via the inlet tube to the glass cell. The inlet valve was typically opened for 2 s to fill ¹⁹⁹Hg

² Brewster plate from Eksmaoptics: $\Theta_b = 55^\circ$ extinction factor $\eta = 1/100$ (see <http://www.eksmaoptics.com>).

³ Hamamatsu R431S.

¹ Fomblin[®] is a registered trademark of Solvay Solexis.

vapor into the cell. In standard operation, the outlet valve opened after the observation of the precession signal and mercury was pumped out of the cell. One such cycle lasted between two and three minutes. Approximately 10 % of the ^{199}Hg vapor remained in the cell. For safety considerations, the mercury that was pumped from the cell was trapped in a mercury filter system made of activated charcoal with sulfur additives.

The cylindrical magnetometer cells (ID = 50 mm; $l = 80$ mm) are made of borosilicate glass (see Fig. 2) and are aligned with the shield axis when installed. The end windows are circular quartz plates (OD = 60 mm, $d = 3$ mm) with a UV transmission of 90 %. A plastic frame compresses O-rings for vacuum tightness between cylinder and end plates. The O-rings (string diameter 1.7 mm) were placed in a 1-mm-deep, 2-mm-wide groove on the rim of the cylinder. In the center of the cell, two glass tubes (ID = 4 mm; $l = 50$ mm) connect the cell to non-magnetic polytetrafluoroethylene (PTFE) valves. The exact position along the z -axis of the cell is given by the length of the aluminum tubes that connect the vacuum/Hg vapor system to the cell.

2.2 Data acquisition

A standard National Instruments NI-USB6211 DAQ card with a 16-bit ADC and a sampling rate of 250 kS/s was used for data acquisition. The signal current of the PMT was grounded over a resistance $R = 1\text{ M}\Omega$. The voltage over this resistance was sampled at 1 kHz and recorded. The card's digital output channels were used for controlling the vacuum valves. One analog output channel was used to supply the current for the B_0 coil. The B_1 coil was



Fig. 2 Glass cell used in the setup. O-rings in machined grooves compressed by the quartz plates guarantee vacuum tightness at both ends (not shown in the image). The two glass tubes connecting the cell to the inlet and outlet valve and are coated with Fomblin oil in all measurements




Fig. 3 Variation in the photomultiplier signal versus time during one cycle, reflecting the five steps: *a* measurement of the noise level for 5 s, *b* chamber filled with mercury (rapid change of DC level from -3.1 V to -2.4 V), *c* polarization of the mercury (slow decrease in the DC level over 30 s), *d* free precession of ^{199}Hg over 60 s, *e* removal of mercury from the cell. The inset shows the oscillating structure of the signal

powered by a separate current supply.⁴ The card and the current supply were controlled by a LabView application. The application was structured in cycles consisting of five steps, which are explained in Fig. 3. The duration of each step could be changed as well as the values for the currents in the coils; normally, the currents remained unchanged. The amount of mercury in the cell was controlled by the opening time of the inlet valve.

3 Anti-relaxation coatings

Very often the most important depolarization mechanism for ^{199}Hg atoms are wall collisions. Most likely, dipolar interactions at paramagnetic sites on the surface lead to depolarization of ^{199}Hg vapor [9]. In order to keep the depolarization rate small, the surface is coated with a non-polar material. So far, Fomblin oil of type “Y” has been used as anti-relaxation coating for the polarization cell of the nEDM experiment at PSI. Fomblin is a perfluorinated polyether consisting of carbon, fluorine, and oxygen atoms. The C–F bonds result in low vapor pressures, and the oil is normally used in vacuum pumps.

In the past, positive results were reported for non-polar paraffin or paraffin-like coatings [9], which can be considered as standard surface coatings in many experiments dealing with polarization of gases and vapors. From our own experience, we knew that perfluorinated hydrocarbons like PTFE or Fomblin oil are good anti-relaxation coatings; hence, we also studied a perfluorinated paraffin from Maflon.⁵ The materials we tested in our setup are listed in

⁴ PL 303-P from Thurlby Thandar Instruments Ltd.

⁵ Maflon: <http://www.maflon.com> (2010).

Table 1 Measured τ -times (first measurement τ_1 , second τ_2) for studied coatings

Coating material and its chemical structure	τ_1 (s)	τ_2 (s)
Perfluorinated paraffin	40.5 (1.2)	34.6 (6)
$C_{20}F_{42}(80\%) + C_{16}F_{34}(10-20\%)$		
Fomblin grease	34.7 (7)	30.6 (5)
$CF_3-[-O-CF_2-CF_2]_n-[-O-CF_2]_m-O-CF_3$ mixed with CF_2-CF_2		
SurfaSil	32.2 (4)	30.6 (7)
$Cl-[-(CH_3)_2-Si-O-]_n-(CH_3)_2-Si-Cl$		
Paraffin	26.3 (4)	28.0 (2)
$C_{32}H_{66}$		
Fomblin oil type "Y"	28.4 (5)	27.0 (6)
$CF_3-[-O-CF_2-CF_2]_n-[-O-CF_2]_m-O-CF_3$ $n/m = 20...40$		
AquaSil	23.0 (1.0)	26.0 (6)
$CH_3-(CH_2)_{15}-Si-(OH)_3$		
Black Teflon	<5	-
CF_2-CF_2 mixed with carbon		
Apiezon "J" oil based on hydrocarbons	No signal	-

The error of the time constants are fit errors scaled for reduced $\chi^2 = 1$. The τ -times measured inside the neutron precession chamber of the nEDM apparatus at PSI are typically $\sim 100-180$ s. It is made of two diamond-like-carbon (DLC)-coated electrodes and a deuterated polysterol (dPS) [14]-coated insulator ring. Note that the neutron precession chamber is much larger and has a mean free path of 19 cm, and hence an average wall collision frequency of 930 Hz, giving similar depolarization rates as in these measurements

Table 1. AquaSil⁶ and SurfaSil⁷ are hydrocarbons containing silicon atoms that react directly with glass and have been reported as potential candidates in Ref. [8]. These solid coatings could make re-coating of the cell unnecessary. The "J" oil from Apiezon⁸ was chosen because it is a well-known vacuum oil that is based on hydrocarbons. Finally, we tested black PTFE, a mixture of PTFE with 25 % carbon to color the material black. We expected that the excellent anti-depolarization properties of PTFE would be maintained, while the black color would significantly reduce the reflection of linear polarized light re-emitted from the ¹⁹⁹Hg atoms during the polarization process. However, it turned out to be completely unsuitable.

3.1 Coating the glass cell

In all cases, the glass cells were first cleaned with water and soap, rinsed with demineralized water and then dried

⁶ AquaSil[®] is a registered trademark of Dentsply.

⁷ SurfaSil[®] is a registered trademark of Siltech LLC.

⁸ Apiezon[®] is a registered trademark of M&I Materials.




Fig. 4 Setup for vacuum deposition of normal and perfluorinated paraffin. 1 Vacuum vessel, 2 window flange to observe progress of evaporation, 3 glass cell with one quartz plate, 4 vacuum valve to pumping unit 5 steel tube for thermal insulation, 6 paraffin, 7 resistive heater, 8 thermometer, 9 pressure gauge

with a hot air gun. Fomblin oil and grease, as well as the "J" oil of Apiezon, were uniformly spread on the inside of the cell with a nitrile-glove-covered finger.

AquaSil and SurfaSil were applied by immersion of the glass cells into a solution of these chemicals. AquaSil was purchased as a 20 % solution in alcohol, which was further diluted in water to a 1 % solution. SurfaSil was diluted in acetone to a 1–10 % solution. In both cases, the cells were immersed for 5–10 s, during which the solutions were continuously stirred with a magnetic stirrer. Afterward, the cells were rinsed thoroughly with methanol to remove the excess, unreacted solution and were dried for 24 h in a fume hood.

The normal and perfluorinated paraffin coatings were applied by evaporation (Fig. 4 shows the evaporation setup). The cells were placed upright on a copper heating plate inside a vacuum vessel. Instead of putting the cell directly on the heating plate, we used a stainless steel ring to provide a thermal insulation and thus help keep the glass cool. In order to obtain an even coating, we repeated the coating process with the cell turned up side down. A small amount (<0.1 g) of paraffin was placed inside the stainless steel ring on top of the copper plate. The cell was then closed off with one of the quartz windows on top. Once the vessel was under vacuum, the heater was turned on to melt the paraffin and start the coating process. Ordinary paraffin melts at ~ 80 °C, while perfluorinated paraffin sublimates at ~ 160 °C. A window on the vacuum vessel allowed us to observe and control the deposition. After ~ 20 min, the paraffin flake had disappeared and the cell was coated.

In all cases, the quartz end windows were coated with the same material during the same process; the two




Fig. 5 The plot shows the photo multiplier signal in volts during several polarization and free precession cycles with varying “dark times”. In each cycle one can distinguish the initial filling of the cell with Hg vapor (sharp signal change from -1.8 to -1.3 V); the polarization of the vapor; the blocking of the light for variable “dark times” between 0 and 60 s (PM signal at 0 V), the free precession

after removing the light block; and the final vacuum pumping of the cell (slow signal decrease from -1.3 to -1.8 V). From the “dark time”-dependent change of the initial free precession amplitude after blocking the readout light, we deduced the depolarization time constant τ

connection tubes were always coated with Fomblin oil and the O-rings with Fomblin grease.

3.2 Measurement of the decay time constants

The depolarization rate of a precessing population of spin polarized atoms is a combination of depolarization due to wall collisions and inhomogeneous magnetic fields:

$$1/\tau = 1/T_2 + 1/\tau_w. \quad (2)$$

Here, T_2 is the transversal polarization decay time constant due to magnetic field inhomogeneities, and τ_w is the decay time constant due to wall interactions. Measured magnetic field maps helped us to estimate $T_2 \approx 200$ s using equation (62) in Ref. [10]. The experiment was performed at ~ 22 °C, which results in a mean velocity $v_{\text{Hg}} \approx 177$ m/s and an average wall collision frequency of $r \approx 4.7$ kHz in the cells.

We measured the relaxation time with an adapted version of the “relaxation in the dark” method pioneered by Franzen [11].⁹ In this method, ^{199}Hg was filled into the chamber and the atoms were optically pumped to the maximum polarization, which was indicated by a maximum light transmission through the magnetometer cell. Then, we non-adiabatically switched on B_1 and blocked the reading light for a “dark time” of $\Delta t = 5 \dots 60$ s, after

which the amplitude of the precession signal was measured. Typically, the initial amplitude after 5-s “dark time” had a signal/noise ratio of ~ 50 . Finally, the cell was pumped for about 100 s to remove the mercury. It is important that the whole measurement was performed with the same ^{199}Hg density, since the polarization depends slightly on the number density. Ideally, one would have filled the cell only once with mercury and never opened the valves during the measurement. However, then the residual pressure would have risen due to out-gassing and small leaks and collisions with residual gas molecules would have distorted the measurement.

This method combines two advantages: (1) we do not have to worry about the influence of the read out light, which might have significantly depolarized the ^{199}Hg ensemble and (2) measuring the amplitude and not the absolute light intensity after the “dark time” makes the method more robust against intensity drifts of the lamp. An example of a measurement is shown in Fig. 5.

The relaxation time, τ , was determined by fitting a single exponential (see Fig. 6) to initial precession amplitudes extracted for different times in the dark. Each coating was measured twice with a time difference of at least 2 weeks between the measurements. During this time, the cells remained untouched and exposed to normal air conditions. The results are summarized in Table 1. From the measured values, it is clear that most of the tested materials are as good as, or even slightly better than, the previously used Fomblin oil. The slight decrease in τ in some of the second measurements might be interpreted as a degradation

⁹ Franzen originally measured the longitudinal depolarization rate T_1 by measuring the increase in the transmitted light intensity after blocking the pump light beam.




Fig. 6 The amplitude of the signal as a function of the dark time t_{dark} . The decay constant τ was extracted from an exponential fit to the data. The example graph shows a measurement of paraffin coating: $\tau = 28(2)$ s, $A = 42(1)$ mV, $y_0 = 0(2)$ with a reduced $\chi^2 = 1.22$

of the surface quality with time or as a change of the magnetic field conditions. The longest τ was measured with perfluorinated paraffin from Maflon, a skiing wax. The “J” oil of Apiezon was found to be highly magnetic, as measured with a fluxgate magnetometer, which explains why no signal was seen. Black PTFE showed a very short τ less than 5 s and was not measured a second time. A possible reason might be contaminants in the material, which cause the ^{199}Hg atoms to depolarize. However, we found no signal ($\Delta B < 20$ pT at a distance of 3 cm) indicative of a magnetic contamination in a measurement with a cesium-magnetometer-based gradiometer [12, 13].

4 Conclusion and discussion

A ^{199}Hg magnetometer test apparatus was built to investigate potential improvements of the ^{199}Hg magnetometer of the nEDM experiment at the Paul Scherrer Institut. As a first study, depolarization times of different magnetometer cell coatings were measured. Several materials showed similar or even longer relative depolarization times than the previously used Fomblin. Previous measurements of Fomblin had an average depolarization probability per wall collision of $\beta_{\text{Fomblin}} = 3.5(5) \times 10^{-6}$ [15], which is within a factor of two of our measurement. A similar discrepancy has been noted for the Fomblin grease measurement where previous studies gave depolarization values of $\beta_{\text{Fo-mGr}} = 2.1 \times 10^{-6}$ [16], also approximately a factor of two smaller. These discrepancies might be explained with depolarization upon collisions with the fluoroelastomer o-rings which were used to seal off the cell, or via collisions with the inner surfaces of the two PTFE valves. For all materials, we took great care that the measurements

were performed under identical conditions. Small variations in the magnetic field environment, which was not monitored during measurements, might have slightly changed the T_2 -time but cannot explain a factor of two. The depolarization time of an uncoated cell was not measured as our experience with the mercury magnetometer inside the nEDM experiment showed worse performances for partially uncoated cells.

Perfluorinated paraffin and SurfaSil were found to be the most interesting candidates and will be further investigated. Both have the important advantage that the coating is of long durability, and re-coating during nEDM measurements might become unnecessary in the future. In general, the perfluorinated materials seem to allow for longer depolarization times than hydrogenated materials. This might be explained by a more pronounced dipolar character of hydrogen bonds. The long-term stability of the solid coatings remains to be investigated. In future studies using the test apparatus, the magnetic field monitoring and control will be improved.

Acknowledgements The authors would like to thank the University of Fribourg atomic physics group for the preparation of ^{204}Hg bulbs and help with the cesium magnetometry. We thank the initial support of this work by TU München, in particular by P. Fierlinger and G. Petzoldt. The authors are grateful for the excellent technical support by F. Burri and M. Meier.

References

1. D. Budker, M. Romalis, *Nat. Phys.* **3**, 227 (2007)
2. S. Lamoreaux, J. Jacobs, B. Heckel et al., *Phys. Rev. Lett.* **59**, 2275 (1987)
3. J. Jacobs, W. Klipstein, S. Lamoreaux et al., *Phys. Rev. Lett.* **71**, 3782 (1993)
4. K. Green, P.G. Harris, P. Iaydjiev et al., *Nucl. Instrum. Methods A* **404**, 381 (1998)
5. M.D. Swallows, T.H. Loftus, W.C. Griffith et al., *Phys. Rev. A* **87**, 012102 (2013)
6. C. Baker, G. Ban, K. Bodek et al., *Phys. Proc.* **17**, 159 (2011)
7. M. Horras, *A highly sensitive Hg magnetometer for the nEDM experiment*. Ph.D. thesis, ETH Zürich (2012)
8. Y. Chibane, *A new magnetometer for the nEDM experiment*. Ph.D. thesis, University of Sussex (1990)
9. M.V. Romalis, L. Lin, *J. Chem. Phys.* **120**, 1511 (2004)
10. G. Cates, S. Schaefer, W. Happer, *Phys. Rev. A* **37**, 2877 (1988)
11. W. Franzen, *Phys. Rev.* **115**, 850 (1959)
12. S. Groeger, A. Pazgalev, A. Weis, *Appl. Phys. B Lasers Optics* **80**, 645 (2005)
13. A.S. Pazgalev, *Lamp-pumped Cs magnetometer test stand user manual*. Fribourg, unpublished (2008)
14. K. Bodek, M. Daum, R. Henneck et al., *Nucl. Instrum. Methods A* **597**, 222 (2008)
15. S. Rocchia, *La comagnétométrie mercure pour la mesure du moment électrique du neutron*. Ph.D. thesis, Université Joseph Fourier, Grenoble I (2009)
16. D.J.R. May, *A high precision comparison of the gyromagnetic ratios of the ^{199}Hg atom and the neutron*. Ph.D. thesis, University of Sussex (1998)